



TILE ADHESIVE, GROUT AND CLEANER



Features



Sag Resistant



Water Resistant




Heat Ageing

JSW TYLFIX TYPE 4

Tile Adhesive for large Glass & Stone Tiles and Dry Wall Boards

AREAS OF APPLICATION


JSW Tyfix Type 4 All types of ceramic tiles, clay tiles, basalt tiles, terracotta, pavers, brick, vitrified tiles, glass mosaic tiles, porcelain tiles, natural stone tiles, large format tiles, marble, large thin/slim tiles, low thickness slabs and also intended for installation on dry wall board substrates like gypsum boards, plywood, MDF board, fiber cement board, bison panel etc.



Kitchen



Bathroom & Toilet



Commercial & Residential



Canteen & Pantry

5 BENEFITS

- Easy to use - just add water on site, ready to use.
- Ideal product for tiles and stone tiles on exterior wall substrates like plaster or concrete.
- Highly polymer modified – provides high adhesion strength to bond with variety of substrates for fixing a variety of tiles and stones.
- Sag resistant formula: provides hassle-free application on vertical walls.
- Sustain heat ageing, making it ideal for high temperature locations.

BEST BEFORE

12 months for sealed pack when stored under cover, out of direct sunlight and damp proof condition.

COVERAGE

- Approx. 5 - 6 m² / 20 kg Bag at 3 mm thickness (using 6 mm x 6 mm notch).
- Approx. 2.5 - 3 m² / 20 kg Bag at 6 mm thickness (using 12 mm x 12 mm notch).
- ***Coverage will vary depending on trowel notch size, type, tile size and substrate smoothness and evenness.**

STANDARD COMPLIANCES

IS: 15477 : 2019 TYPE 4 'T S1', C2TES1 (Cementitious improved performance slip resistant, deformable adhesive with extended open time) as per EN12004:2017/ISO 13007.

World's No.1 Eco Friendly Cement Company

TECHNICAL SPECIFICATIONS

Properties	Results
Tentative mixing ratio (Powder: Water)	3.5 : 1 by volume; 1 : 0.22 by weight
Mixed density	1.8 – 2.0 kg/ ltr
Table flow	Max. 190
Open time (IS 15477 : 2019)	Approx. 40 minutes
Adjustability (IS 15477 : 2019)	Approx. 30 minutes
Pot life	Approx. 120 minutes
Tensile adhesion strength as per IS15477 : 2019	≥ 1.5 N/mm ²
Application temperature (substrates & materials)	5°C to 35°C
Adhesive thickness	3 - 12 mm
Setting/ trafficable time	24 hours

PACK SIZE

20 kg



JSW TYLFIX TYPE 4

TILE ADHESIVE, GROUT & CLEANER

MARKETED BY: JSW Green Cement Pvt. Ltd.
Babukhan Millenium Centre, 6-3-1099/1100, No. 702, Block-A, Somajiguda, Hyderabad, Telangana, India, Pincode - 500 082.

Email: info@jswcement.in | Website: www.jswcement.in | Toll free - 18002662661

