



JSW Cement Ltd

P.O. Vidyanagar, Tq : Sandur,
Dist. Ballari - 583275 Karnataka, India
Phone : 08395-241001
Fax : 08395-241003
Website : www.jsw.in

CIN - U26957MH2006PLC160839



TC-11908



ISO 9001, ISO 14001, ISO 50001 & OHSAS 18001
Certified by IRQS

IS 16415:2015



CM/L-6200134386

TEST REPORT

		ULR	TC-119082300000014F
Customer Name & Address:	Marketing JSW CEMENT LTD PO Vidyanagar, Tornagallu, Bellary 583275 , Karnataka	Date Of Issue :	12.09.2023
Let. Ref. No :	NA	Sample Received Date :	13.08.2023
Type of Sample :	CC	Sample Ref ID :	JSW/VNR/ 697 WEEK No:32
Sample Description :	Composite Cement	Duration of Testing :	14.08.2023 to 11.09.2023
Condition of sample :	UNSEALED	Test Method :	IS: 4032-1985 IS: 4031-1988
Environmental Condition Duration of Testing :	Temperature: 28 °C	Relative Humidity :	67 %

TEST RESULT CHEMICAL PARAMETERS

Sr. No	Test Parameters	Test Method	Unit	Results	Requirement IS: 16415-2015
1	Insoluble Residue (% by mass)	IS: 4032-1985	%	15.23	Minimum 15.0 % -Maximum 35.0 %
2	Magnesia Oxide (MgO),(%by mass)	IS: 4032-1985	%	3.05	Maximum 8.0 %
3	Sulphur Trioxide (SO3)(%by mass)	IS: 4032-1985	%	1.77	Maximum 3.5 %
4	Sulphide Sulphur (% by mass)	IS: 4032-1985	%	0.17	Maximum 0.75 %
5	Loss on Ignition (% by mass)	IS: 4032-1985	%	2.86	Maximum 5.0 %
6	Chloride Content(%by mass)	IS: 4032-1985	%	0.013	Maximum 0.10 %
7	Alkali Content(%) as Na2O	IS: 4032-1985	%	0.39	Maximum 0.6 %





JSW Cement Ltd

P.O. Vidyanagar, Tq : Sandur,
Dist. Ballari - 583275 Karnataka, India
Phone : 08395-241001
Fax : 08395-241003
Website : www.jsw.in

CIN - U26957MH2006PLC160839



TC-11908



ISO 9001, ISO 14001, ISO 50001 & OHSAS 18001
Certified by IRQS

IS 16415:2015



CM/L-6200134386

TEST REPORT PHYSICAL PARAMETERS

					ULR	TC-119082300000014F
Sr. No	Test Parameters	Method of tests	Unit	Results	Requirement IS: 16415-2015	
1	Consistency	IS 4031(Part 4)-1988	%	30.00	Not specified	
2	Fineness	IS 4031(Part 2)-1999	M ² /Kg	354	Shall not be less than 300 m ² /kg	
3	Initial Setting Time	IS 4031(Part 5)-1988	Minutes	150	Shall not be less than 30 Minutes	
4	Final Setting Time	IS 4031(Part 5)-1988	Minutes	250	Shall not be more than 600 Minutes	
5	Soundness (by Le-Chateliers)	IS 4031(Part 3)-1988	mm	1.16	Shall not be more than 10 mm	
6	Soundness (by Autoclave)	IS 4031(Part 3)-1988	%	0.012	Shall not be more than 0.8 %	
7	Compressive Strength; a) 72 ± 1h(3 days) b) 168 ± 2h(7 days) c) 672 ± 4h(28 days)	IS 4031(Part 6)-1988	Mpa	20.60 32.77 54.12	Shall not be less than 16.0 Mpa Shall not be less than 22.0 Mpa Shall not be less than 33.0 Mpa	
8	Drying shrinkage	IS 4031(Part 10)-1988	%	0.01	Maximum 0.15 %	

- Note:
- 1) This report is based on the sample received by our laboratory.
 - 2) The test result relates only to the item tested.
 - 3) This report shall not be reproduced, except in full, without the written permission of our Laboratory.
 - 4) Statement of conformity to a specification is provided considering the level of risk associated with decision
 - 5) Measurement Uncertainty is not taken into consideration while stating conformity with the specified requirements as requested by the customer.
 - 6) Any correction invalidates this report.


Reviewed and Authorized Signature

Name:

Designation:

END OF THE REPORT

Page 02 of 02



Part of O.P. Jindal Group

Regd. Office: JSW Center,
Bandra Kurla Complex,
Bandra (East), Mumbai 400051
Phone: 022-42461000
Fax : 022-26502001