



CM/L-5710037013

**JSW CEMENT LTD.,
SALBONI, WEST MIDNAPORE, WESTBENGAL**



TEST CERTIFICATE FOR PORTLAND SLAG CEMENT

S.No.	Characteristics	Requirement as Per IS 455:2015	Test Result
	CHEMICAL REQUIREMENTS	% Max.	
1	Magnesium Oxide (% MgO)	10.0	3.87
2	Sulphur Trioxide (% SO ₃)	3.5	1.70
3	Sulphide Sulphur (% S)	1.5	0.16
4	Loss On Ignition (%)	5.0	1.47
5	Insoluble Residue (%)	4.0	1.07
6	Chlorides (%)	0.1	0.005
	PHYSICAL REQUIREMENTS		
1	Fineness (M ² /Kg)(Min)	225	390
2 a	Normal Consistency (%)		32.00
b	Setting Time (minutes)	30	175
	a) Initial(Min)	600	260
	b) Final(Max)		
3	Soundness		
	a) Le-chatelier (mm)(Max)	10	0.500
	b) Auto Clave (%) (Max)	0.8	0.029
4	Compressive Strength (MPa)		
	a) 72 ± 1h (3 days)(Min)	16	29.11
	b) 168 ± 2h(7 days)(Min)	22	39.17
	c) 672 ± 4h (28 days)(Min)	33	54.30

Remarks: Temperature during testing is 27+/-2degree centigrade.
Specific Gravity: -2.97

**WEEK NO: 38
17.09.2023 – 23.09.2023**

JSW CEMENT Ltd.

Authorized Signatory